



中国认可
国际互认
检测
TESTING
CNAS L0699



TEST REPORT

CEPRI-EETC02-2022-0036(E)

Client: ZGHD ELECTRIC CO.,LTD

Object: 35kV AC shielded rear connected gapless metal
oxide lightning arrester

Type: GHD-35BLQ-51/134

Test Category: Type Test

**POWER INDUSTRY QUALITY INSPECTION AND TEST
CENTER FOR ELECTRIC EQUIPMENT**



NOTICE

1. This report will enter into effect with seals of test center.
2. This report is legally made available accompany with compiled, checked, verified and approved signatures.
3. Alter the report is invalid.
4. This report only takes responsibility to the test object.
5. Part of copy is invalid.
6. Any objections in the report should be posed within 15 days once the report is received.
7. The inspection and testing management system of China Electric Power Research Institute includes the following institutes:

National Wind Power Integration Research and Test Center

☆ **Power Industry Quality Inspection and Test Center for Electric Equipment**

Power Industry Quality Inspection & Test Center for Electric Power Equipment and Instruments

Power Industry Quality Inspection & Test Center for Electrical Material and Components

Power Industry Quality Inspection & Test Center for Automation Equipment

Power Industry Quality Inspection & Test Center for Communication Equipment

Power Industry Quality Inspection & Test Center for Concrete Power and Communication Poles

Power System Electromagnetic Compatibility and Electromagnetic Environmental Research and Monitoring Center

Address: NO.143, Luoyu Road, Hongshan District, Wuhan, Hubei Province, 430074.


Fax: 86-27-5937-8488 Service line: 400-656-5689 Supervision hotline: 010-82813498




E-mail: eetc@epri.sgcc.com.cn

Website: <http://www.epri.sgcc.com.cn>

Catalogue

1.Catalogue.....	1
2.Signature Page.....	2
3.Test Results.....	3
4.Content.....	4
5.Appendix A Object Parameters.....	15
6.Appendix B The Main Test Devices.....	15
7.Appendix C Waveforms.....	16
8.Appendix D Visual and dimensional check.....	19



Test Report	Power Industry Quality Inspection and Test Center for Electric Equipment		CEPRI-EETC02-2022-0036(E) Total 20 Page 2
Client	ZGHD ELECTRIC CO.,LTD	Manufacturer	ZGHD ELECTRIC CO.,LTD
Object	35kV AC Shielded rear connected gapless metal oxide lightning arrester	Type	GHD-35BLQ-51/134 (Φ42mm×24mm)
Sampling procedure	By the client delivery	Serial No.	1 arrester (001) 4 dielectrically prorated sections(101~104) 10 thermally prorated sections (201~210) 13 resistors (301~313) 1 housing(401)
Test Category	Type Test	Date	2022.04.25~2022.06.28
Requirements	GB/T 11032-2020 Metal-oxide surge arresters without gaps for a.c. systems		
Conclusion	The 35kV AC Shielded rear connected gapless metal oxide lightning arrester type GHD-35BLQ-51/134 have successfully passed the type test specified in GB/T 11032-2020.		
Note	Note :See appendix A for sample instruction.		
Tested by: 万克			梁菊霞 
Checked by: 王陆璐			Verified by: 左中秋 
Approved by: 王保山			Date of issue: 2022-08-18



Test Results

No.	Item	Requirements	Results	Evaluation	
1	D.C. reference voltage test	$73.0\text{kV} \leq U_{1\text{mADC}} \leq 76.5\text{kV}$	75.5kV	Pass	
2	Leakage current test at 0.75 times D.C. reference voltage	$I_L(0.75U_{1\text{mADC}}) \leq 50\mu\text{A}$	5 μA	Pass	
3	Continuous operating current test	$I_x \leq 1000\mu\text{A}$ $I_R \leq 200\mu\text{A}$	$I_x = 197\mu\text{A}$ $I_R = 82\mu\text{A}$	Pass	
4	A.C. reference voltage test	$U_{1\text{mAAC}} \geq 51.0\text{ kV}_p / \sqrt{2}$	$55.62\text{kV}_p / \sqrt{2}$	Pass	
5	Partial discharge test	$1.05U_c$ 下, $PD \leq 10\text{ pC}$	$PD = 2.2\text{ pC}$	Pass	
6	Insulation withstand tests on the arrester housing	Power-frequency voltage: Dry $\geq 95\text{ kV}_{\text{rms}}$, for 1min. Lightning impulse voltage : 185kV_p , the positive and negative 15 times respectively.	Power-frequency voltage dry: $95.1\text{kV}_{\text{rms}}$, 1min. Lightning impulse voltage: $185.2\text{kV}_p \sim 186.1\text{kV}_p$ the positive and negative 15 times respectively.	Pass	
7	Residual voltage test	Lightning impulse	$\leq 134.0\text{kV}_p$	125.39kV_p	Pass
		Switching impulse	$\leq 114.0\text{kV}_p$	99.89kV_p	
		Steep current	$\leq 154.0\text{kV}_p$	132.53kV_p	
8	Repetitive charge transfer withstand test	10 samples should withstand 20 times 2ms long-duration current impulse and the charge value should not less than 0.3C.	$0.330\text{C} \sim 0.340\text{C}$	Pass	
9	Test to verify long term stability under continuous operating voltage	The accelerated ageing test of resistors should be carried out according to the specified procedure.	$P_{\text{max}} \leq 1.3P_{\text{min}}$, $P_{\text{all.max}} \leq 1.1P_{\text{start}}$; the samples fulfilled the requirements.	Pass	
10	Heat dissipation behavior verification test	The test section is for all instants during the cooling period have a temperature higher than the complete arrester.	Fulfilled the requirements. See fig 2.	Pass	



No.	Item	Requirements	Results	Evaluation																		
11	Operating duty test	Long-duration current impulse 2 times. Rated thermal energy injection $Q_{th} \geq 0.7 C$ The residual voltage shall not have changed by more than 5%.	$Q_{th} \geq 0.717C$ The residual voltage changed ratio is from +0.59%~+1.07%	Pass																		
12	Power-frequency voltage-versus-time characteristics	$Q_{th} \geq 0.7C$ Supply the Power frequency voltage-versus-time characteristics for the range of voltage from $1.20U_r^*$ to $1.00U_r^*$, the range of time from 0.1s to 1200s for with prior duty, $1.20U_r^*$ to $1.00U_r^*$, the range of time from 1.1s to 1200s for without prior duty.	<table style="width:100%; border-collapse: collapse;"> <tr> <td style="width:50%;">$Q_{th} \geq 0.721C$</td> <td style="width:50%;"></td> </tr> <tr> <td>With prior duty test</td> <td></td> </tr> <tr> <td>$1.20U_r^*$ 0.1s</td> <td></td> </tr> <tr> <td>$1.15 U_r^*$ 1.1s</td> <td></td> </tr> <tr> <td>$1.10 U_r^*$ 10.1s</td> <td></td> </tr> <tr> <td>$1.00 U_r^*$ 1200s</td> <td></td> </tr> <tr> <td>Without prior duty test</td> <td></td> </tr> <tr> <td>$1.20 U_r^*$ 1.1s</td> <td></td> </tr> <tr> <td>$1.00 U_r^*$ 1200s</td> <td></td> </tr> </table>	$Q_{th} \geq 0.721C$		With prior duty test		$1.20U_r^*$ 0.1s		$1.15 U_r^*$ 1.1s		$1.10 U_r^*$ 10.1s		$1.00 U_r^*$ 1200s		Without prior duty test		$1.20 U_r^*$ 1.1s		$1.00 U_r^*$ 1200s		Pass
$Q_{th} \geq 0.721C$																						
With prior duty test																						
$1.20U_r^*$ 0.1s																						
$1.15 U_r^*$ 1.1s																						
$1.10 U_r^*$ 10.1s																						
$1.00 U_r^*$ 1200s																						
Without prior duty test																						
$1.20 U_r^*$ 1.1s																						
$1.00 U_r^*$ 1200s																						
13	Test to verify the dielectric withstand of the internal components of an arrester	1 time 65kA-4/10 μ s	66.90kA, no puncture, flashover, cracking or other significant damage.	Pass																		

(No content in this page below)



质量
报
章

Test Report	Power Industry Quality Inspection and Test Center for Electric Equipment	CEPRI-EETC02-2022-0036(E) Total 20 Page 5
--------------------	---	--

Content:

1~2 D.C. reference voltage test and leakage current at 0.75 times D.C. reference voltage test

Environment temperature:21.0°C humidity:74%

Samples	D.C. reference voltage U_{1mADC} kV		0.75times D.C. reference voltage kV		Leakage current μA	
	Measured value	Specified value	Measured value	Specified value	Measured value	Specified value
	001	75.5	$73.0 \leq U_{1mADC} \leq 76.5$	56.6	$0.75U_{1mADC} \pm 1\%$	5

Note: The standard only provides the D.C. reference voltage lower limit. The upper limit declared by the manufacturer is used to determine the proportion of the arrester protection level.

Fulfilled the requirements.

3~4 Power-frequency reference voltage test and Continuous current test

Environment temperature:21.0°C humidity:74%

Samples	The power-frequency reference voltage U_{1mAAC} $kV_p/\sqrt{2}$		I_R μA_p		I_X μA_{rms}	
	Measured value	Specified value	Measured value	Specified value	Measured value	Specified value
	001	55.62	≥ 51.0	82	≤ 200	197

Note1: The client claims the power frequency reference current is 1mA.

Note2: The standard specifies the continuous current through the arrester shall not exceed the manufacturer's declared value.

Fulfilled the requirements.

5 Partial discharge test

Samples	U_r	U_r duration time	$1.05U_c$	$1.05U_c$ duration time	Partial discharge
	kV_{rms}	s	kV_{rms}	s	pC
001	51.0	10	42.8	60	2.2
specified value	51.0	2~10	42.8	60	≤ 10

Fulfilled the requirements.



Test Report	Power Industry Quality Inspection and Test Center for Electric Equipment	CEPRI-EETC02-2022-0036(E) Total 20 Page 6
--------------------	---	--

6 Insulation withstand tests on the arrester housing

6.1 Power frequency voltage withstand test

t=31.0°C RH=40% Atmospheric pressure: 100.1kPa

Samples	Specified value	Applied voltage	Duration	Test result
	kV _{rms}	kV _{rms}	s	
401	95.0(dry)	95.1	60	No flashover

Fulfilled the requirements.

6.2 Lightning impulse voltage withstand test

t=31.0°C RH=40% Atmospheric pressure: 100.1kPa

Samples	Specified value		Applied voltage	Withstand times	Test result
		kV	kV _p		
401	(+) 185	185	185.2~185.8	15	no flashover
	(-) 185	185	185.2~186.1	15	no flashover

Fulfilled the requirements.

(No content in this page below)



Test Report	Power Industry Quality Inspection and Test Center for Electric Equipment	CEPRI-EETC02-2022-0036(E) Total 20 Page 7
--------------------	---	--

7 Residual voltage test

7.1 Lightning impulse current residual voltage test

Samples			301	302	303
Resistor	U_{1mADC}	kV	5.07	5.07	5.07
	8/20 μ s, 2.5kA	kV _p	7.82	7.80	7.81
	8/20 μ s, 5kA	kV _p	8.31	8.30	8.31
	8/20 μ s, 10kA	kV _p	9.05	9.03	9.03
	U_{5kA}/U_{1mADC}	-	1.64	1.64	1.64
Complete arrester	U_{1mADC}	kV	$73.0 \leq U_{1mADC} \leq 76.5$		
	Scale coefficient	-	15.09	15.09	15.09
	8/20 μ s, 2.5kA	kV _p	117.99	117.69	117.84
	8/20 μ s, 5kA	kV _p	125.39	125.24	125.39
	8/20 μ s, 10kA	kV _p	136.55	136.25	136.25
	Lightning impulse protection level	kV _p	125.39		
	Specified value	kV _p	≤ 134.0		

Note 1: Shunt 0.025 V/A, divider $K_d=206.8$

Note 2: According to the determined residual pressure, draw the residual voltage and current curve, in the curve corresponding to the nominal discharge current read residual voltage, defined as the lightning protection lightning protection level.

7.2 Switching impulse current residual voltage test

Samples			301	302	303
Resistor	Residual voltage at 250A	kV _p	6.62	6.61	6.61
Complete arrester	Test value	kV _p	99.89	99.74	99.74
	Switching impulse current residual voltage	kV _p	99.89		
	Specified value	kV _p	≤ 114.0		

Note: Shunt 0.025 V/A, divider $K_d=206.8$

7.3 Steep current impulse residual voltage test

Samples			301	302	303
Resistor	5 kA U_{res1}	kV _p	8.97	8.98	8.96
	5 kA U_{res2}	kV _p	0.23		
	U_{res2}/U_{res1}	%	2.6	2.6	2.6
	$U_{res1}-U_{res2}$	kV _p	8.74	8.75	8.73
Complete arrester	Scale coefficient	-	15.09	15.09	15.09
	Residual voltage for the arrester	kV _p	131.88	132.03	131.72
	Inductance per unit length	μ H/m	0.3		
	Height without resistors	m	$0.454-(0.024 \times 5)=0.334$		
	Inductive voltage correction	kV _p	$0.3 \times 0.334 \times 5=0.5$		
	After correction	kV _p	132.38	132.53	132.23
	Residual voltage for the arrester after correction	kV _p	132.53		
Specified value	kV _p	≤ 154.0			

Note1: Shunt 0.0267V/A, divider $K_d=59.8$ 。

Note 2: If U_{res2}/U_{res1} is less than 2%, there is no need to correct Inductive effect.

Fulfilled the requirements. Test waveform is shown in appendix C fig C.1~ fig C.3.



Test Report	Power Industry Quality Inspection and Test Center for Electric Equipment	CEPRI-EETC02-2022-0036(E) Total 20 Page 8
--------------------	---	--

8 Repetitive charge transfer withstand

Samples: 10 resistors (304~313)

Requirements of standards: The samples should withstand more than 0.3C by 8/20us current impulse for 20 times, and after test, have no breakdown or flashover or breakage, the change of residual voltage within $\pm 5\%$, the change of reference voltage within $\pm 5\%$, also should withstand capability to one 8/20us current impulse of at least 0.5 kA/cm² peak current density or 2 times I_n , whichever is lower.

Test data: Fulfilled the requirements, the test waveforms were shown in appendix C fig C.4.

Samples		304	305	306	307	308	309	310	311	312	313
Before test	U_{1mAAC} , kV	3.72	3.73	3.75	3.72	3.70	3.69	3.75	3.73	3.75	3.77
	$8/20\mu s U_{5kAp}$, kV	8.31	8.35	8.37	8.30	8.27	8.25	8.38	8.36	8.38	8.41
Q_{rs} , C		Q_{rs} (Claimed repetitive charge transfer rating) $\times 1.1=0.33$									
1 st	Q_{rs} , C	0.333	0.339	0.337	0.331	0.331	0.334	0.334	0.332	0.336	0.337
2 nd	Q_{rs} , C	0.332	0.337	0.332	0.335	0.331	0.336	0.336	0.335	0.333	0.333
3 rd	Q_{rs} , C	0.331	0.336	0.332	0.334	0.333	0.333	0.333	0.339	0.332	0.332
4 th	Q_{rs} , C	0.337	0.333	0.335	0.335	0.331	0.335	0.337	0.330	0.332	0.333
5 th	Q_{rs} , C	0.338	0.336	0.331	0.337	0.330	0.333	0.334	0.335	0.332	0.331
6 th	Q_{rs} , C	0.340	0.335	0.339	0.331	0.335	0.333	0.335	0.335	0.335	0.332
7 th	Q_{rs} , C	0.330	0.335	0.337	0.340	0.340	0.331	0.330	0.337	0.335	0.336
8 th	Q_{rs} , C	0.338	0.332	0.330	0.336	0.338	0.340	0.337	0.337	0.336	0.332
9 th	Q_{rs} , C	0.336	0.335	0.339	0.331	0.335	0.336	0.332	0.335	0.330	0.336
10 th	Q_{rs} , C	0.339	0.334	0.339	0.335	0.337	0.336	0.335	0.331	0.333	0.335
11 th	Q_{rs} , C	0.335	0.339	0.335	0.334	0.340	0.333	0.334	0.336	0.330	0.337
12 th	Q_{rs} , C	0.335	0.338	0.339	0.331	0.331	0.336	0.333	0.338	0.330	0.335
13 th	Q_{rs} , C	0.337	0.339	0.332	0.337	0.338	0.335	0.337	0.337	0.334	0.331
14 th	Q_{rs} , C	0.339	0.335	0.337	0.333	0.336	0.336	0.330	0.340	0.338	0.331
15 th	Q_{rs} , C	0.339	0.331	0.333	0.336	0.334	0.338	0.332	0.339	0.336	0.334
16 th	Q_{rs} , C	0.336	0.336	0.335	0.339	0.336	0.330	0.331	0.336	0.335	0.338
17 th	Q_{rs} , C	0.332	0.333	0.334	0.333	0.334	0.339	0.333	0.335	0.335	0.336
18 th	Q_{rs} , C	0.336	0.330	0.332	0.337	0.332	0.339	0.337	0.338	0.333	0.335
19 th	Q_{rs} , C	0.332	0.332	0.336	0.333	0.340	0.339	0.334	0.338	0.331	0.337
20 th	Q_{rs} , C	0.340	0.340	0.331	0.340	0.332	0.333	0.339	0.335	0.333	0.338



Test evaluation	One 8/20 current impulse, kA	6.92 kA $(0.5\text{kA}/\text{cm}^2=0.5 \times 3.14 \times (4.2/2)^2=6.92\text{kA}$ which is lower than 2 times I_n)									
		6.96	6.97	6.95	6.93	6.95	6.96	6.94	6.93	6.96	6.96
	U_{1mAAC} , kV	3.77	3.79	3.82	3.78	3.75	3.76	3.80	3.80	3.82	3.81
	Change rate, %	+1.34	+1.61	+1.87	+1.61	+1.35	+1.90	+1.33	+1.88	+1.87	+1.06
	$8/20\mu\text{s}$ U_{5kAP} , kV	8.40	8.42	8.43	8.37	8.35	8.36	8.45	8.47	8.46	8.49
	Change rate, %	+1.08	+0.84	+0.72	+0.84	+0.97	+1.33	+0.84	+1.32	+0.95	+0.95
Visual inspection	All the samples have no puncture, flashover or cracking.										

Note: Shunt 0.00192V/A.

9. Test to verify long term stability under continuous operating voltage

Samples: 3 dielectrically prorated sections(101~103)

Requirements of standards: 3 resistors should pass the accelerated ageing test.

Test data: Fulfilled the requirements, the accelerated ageing curves were shown in fig 1.

Samples	101	102	103
U_{1mADC} , kV	5.04	5.06	5.02
U_c , kV _{rms}	3.04	3.04	3.04
Charge rate,%	85.0	85.0	85.1
Power losses P_{start} , 3h, W	0.590	0.523	0.586
Power losses P_{100h} , W	0.570	0.502	0.539
Power losses P_{200h} , W	0.595	0.518	0.556
Power losses P_{300h} , W	0.586	0.509	0.553
Power losses P_{400h} , W	0.593	0.515	0.558
Power losses P_{500h} , W	0.562	0.492	0.522
Power losses P_{600h} , W	0.575	0.500	0.508
Power losses P_{700h} , W	0.567	0.494	0.523
Power losses P_{800h} , W	0.559	0.489	0.518
Power losses P_{900h} , W	0.587	0.508	0.537
Power losses P_{end} , 1000+8h,W	0.557	0.484	0.502
P_{min} , W	0.557	0.484	0.502
Any increase of power losses from P_{min} during the remaining test period, P_{max}	0.557	0.484	0.502
$P_{all,max}$, W	0.595	0.523	0.586
$P_{max} / 1.3P_{min}$	0.769	0.770	0.770
$P_{all,max} / 1.1 P_{start}$	0.917	0.910	0.909

Note: (1) Because $P_{max} \leq 1.3P_{min}$, $P_{all,max} \leq 1.1P_{start}$, the samples fulfilled the requirements.
(2) The temperature of blocks: 115 ± 4 °C.






Fig 1 Accelerated ageing test curve

10 Heat dissipation behavior verification of test sample

Samples: 1 thermally prorated section (210) 1 arrester (001)

Requirements of standards: the MO resistors in the sample shall be heated to 140°C by the application of power-frequency voltage. When the temperature is reached, the voltage source shall be disconnected and the cooling time curve shall be determined. At any time, the measured cooling curve of section falls shall above the measured cooling curve of the arrester.

Test data: Fulfilled the requirements, the test waveform was shown in fig 2.




Fig 2 The cooling curve for the section and arrester

盗
测
之
月



Test Report		Power Industry Quality Inspection and Test Center for Electric Equipment		CEPRI-EETC02-2022-0036(E) Total 20 Page 11		
11 Operating duty test						
Samples: 3 thermally prorated sections (201~203)						
Requirements of standards: 3 thermally prorated sections should pass the high current impulse operating duty test.						
Test data: Fulfilled the requirements, the test waveforms were shown in appendix C fig C.5.						
Samples		201	202	203		
U _{1mADC} , kV		5.11	5.11	5.12		
U _{sr} , kV _{rms}		3.57	3.57	3.57		
U _{sc} , kV _{rms}		2.86	2.86	2.86		
8/20μs, U _{5kA} ,before, kV		8.43	8.42	8.46		
Conditioning test	1 st high current impulse, kA		65.6	64.8	65.2	
	2 nd high current impulse, kA		65.2	65.5	64.9	
preheated samples		preheated samples to 85.0°C±3°C				
Rated thermal energy injection, Q _{th}	Lightning current impulse	1 st Q _{th} ,C	0.362	0.365	0.361	
		2 nd Q _{th} ,C	0.358	0.361	0.356	
	Q _{th} rating (2 times), C		0.720	0.726	0.717	
Applied voltage after the 3 rd impulse	Time	Req.	as short as possible (within 100ms)			
		Actual	86	84	84	
	Applied voltage and duration	U [*] _{sr} , kV _{rms}		3.57	3.57	3.57
		Duration, s		10	10	10
		U [*] _{sc} , kV _{rms}		2.86	2.86	2.86
Duration, min		30	30	30		
Power loss, W	1 s		4.27	4.63	4.37	
	5 min		2.51	2.68	2.56	
	10 min		2.02	2.22	2.11	
	15 min		1.81	2.01	2.01	
	20 min		1.73	1.85	1.93	
	25 min		1.65	1.78	1.88	
	30 min		1.62	1.75	1.86	
Samples cooled to		cooled to ambient 20°C±15°C				
8/20μs, U _{5kA} ,after, kV		8.48	8.51	8.53		
Variability of the residual voltage, %		+0.59	+1.07	+0.83		
Visual inspection		No puncture, flashover, cracking or other significant damage				



质量
报
章

Test Report	Power Industry Quality Inspection and Test Center for Electric Equipment	CEPRI-EETC02-2022-0036(E) Total 20 Page 12			
--------------------	---	---	--	--	--

12 Power-frequency voltage-versus-time test

12.1 Power-frequency voltage-versus-time test data (with prior duty)

Samples			204	205	206	207
U _{1mADC} , kV			5.12	5.13	5.13	5.14
U _{sr} , kV _{rms}			3.58	3.58	3.58	3.59
U _{sc} , kV _{rms}			2.86	2.87	2.87	2.87
8/20μs, U _{5kA} , before, kV			8.45	8.47	8.48	8.48
preheated samples			preheated samples to 85°C±3°C			
2ms long-duration current impulse	1 st impulse	Q _{th} , C	0.363	0.361	0.359	0.365
	2 nd impulse	Q _{th} , C	0.368	0.362	0.362	0.363
	Q _{th} rating (2 times), C		0.731	0.723	0.721	0.728
Applied voltage after the 3 rd impulse	Time	Req.	as short as possible (within 100ms)			
		Actual	84	86	86	88
	Applied voltage and duration	U [*] _{sr} , kV _{rms}	4.29	4.12	3.94	3.59
		TOV scale	1.20	1.15	1.10	1.00
		Duration, s	0.1	1.10	10.1	1200
		U [*] _{sc} , kV _{rms}	2.86	2.87	2.87	2.87
		Duration, min	30	30	30	30
Power loss, W	1 s	8.21	6.58	4.96	4.17	
	5 min	5.36	5.06	2.79	2.62	
	10 min	4.17	3.95	2.53	2.18	
	15 min	3.39	3.07	2.31	1.95	
	20 min	2.75	2.66	2.24	1.95	
	25 min	2.51	2.47	2.18	1.83	
	30 min	2.46	2.41	2.16	1.80	
Samples cooled to			cooled to ambient 20°C±15°C			
8/20μs, U _{5kA} , after, kV			8.57	8.53	8.57	8.55
Variability of the residual voltage, %			+1.42	+0.71	+1.06	+0.83
Visual inspection			No puncture, flashover, cracking or other significant damage			
Fulfilled the requirements, the test waveforms were shown in appendix C fig C.6~C.8.						



Test Report	Power Industry Quality Inspection and Test Center for Electric Equipment	CEPRI-EETC02-2022-0036(E) Total 20 Page 13
--------------------	---	---

12.2 Power-frequency voltage-versus-time test data (without prior duty)

Samples		208	209	
U _{1mADC} , kV		5.12	5.12	
U _{sr} , kV _{rms}		3.58	3.58	
U _{sc} , kV _{rms}		2.86	2.86	
8/20μs, U _{5kA} ,before, kV		8.45	8.46	
preheated samples		preheated samples to 85.0°C±3°C		
Applied voltage	Applied voltage and duration	U _{sr} [*] , kV _{rms}	4.29	3.58
		TOV scale	1.20	1.00
		Duration, s	1.1	1200
		U _{sc} [*] , kV _{rms}	2.86	2.86
		Duration, min	30	30
Power loss, W	1 s	2.85	2.56	
	5 min	2.52	2.17	
	10 min	2.36	1.85	
	15 min	2.19	1.79	
	20 min	2.07	1.74	
	25 min	1.98	1.70	
	30 min	1.90	1.69	
Samples cooled to		cooled to ambient 20°C±15°C		
8/20μs, U _{5kA} ,after, kV		8.42	8.52	
Variability of the residual voltage, %		-0.36	+0.71	
Visual inspection		No puncture, flashover, cracking or other significant damage		

Fulfilled the requirements, the test waveforms were shown in appendix C fig C.9.

(No content in this page below)



Test Report	Power Industry Quality Inspection and Test Center for Electric Equipment	CEPRI-EETC02-2022-0036(E) Total 20 Page 14
--------------------	---	---

13 Test to verify the dielectric withstand of the internal components of an arrester

Samples: 1 dielectrically prorated section (104)

Requirements of standards: preheat the sample to 60°C, consists of one application of a 65kA high-current impulse.

There should be no evidence of a dielectric breakdown. The test waveforms were shown in appendix C fig C.10.

Sample	104		
U_{1mAAC} , kV	3.73		
8/20 μ s, U_{5kA} , before, kV	8.35		
preheated samples	preheated samples to 60°C±3°C		
high-current impulse, kA	66.90		
Samples cooled to	cooled to ambient 20°C±15°C		
8/20 μ s, U_{5kA} , after, kV	8.41		
Variability of the residual voltage, %	+0.72		
Visual inspection	The block can not remove from the section	8/20 μ s current impulse, 2 times	6.92 kA ($0.5kA/cm^2=0.5 \times 3.14 \times (4.2/2)^2=6.92kA$ which is lower than 2 times I_n)
		1 st impulse, kA _p	6.95
		2 nd impulse, kA _p	6.98
		Curve check	No puncture, flashover, cracking or other significant damage

(No content in this page below)



Appendix A: Object ParametersRated voltage U_r : 51kVContinuous operating voltage U_c : 40.8kV_{rms}Nominal discharge current I_n : 5kALightning impulse residual voltage: U_{res} : $\leq 134kV_p$

High-current impulse: 65kA

Claimed repetitive charge transfer rating: 0.3C

Sample instruction:

- 1) 1 arrester, number EETC02-22/02/10-0036-001, short for 001 in report;
- 2) 10 thermally prorated sections, number EETC02-22/02/10-0036-201~EETC02-22/02/10-0036-210 short for 201~210 in report;
- 3) 13 resistors, number EETC02-22/02/10-0036-301~EETC02-22/02/10-0036-313, short for 301~313 in report;
- 4) 1 housing, number EETC02-22/02/10-0036-401, short for 401 in report.;
- 5) 4 dielectrically prorated sections, number EETC02-22/02/10-0036-101~EETC02-22/02/10-0036-104, short for 101~104 in report.

Appendix B: Main test device

NO.	Device name	Device NO.	Measurement	Uncertainty /Accuracy	Calibration institution	Expiration date
1	impulse current generator	EETC02-0003	8/20 μ s 40 kA 4/10 μ s 130 kA	$U_{rel}=0.015 k=2$ $U_{rel}=0.021 k=2$	National center for high voltage measurement	2023-06-23
2	impulse current generator	EETC02-0005	8/20 μ s 40 kA , 30kV 30/80 μ s 2 kA , 30kV	$U_{rel}=0.015 k=2$ $U_{rel}=0.018 k=2$	National center for high voltage measurement	2023-06-29
3	1/5 μ s impulse current generator	EETC02-0004	1/5 μ s 20kA , 20kV	$U_{rel}=0.015 k=2$ $U_{rel}=0.018 k=2$	National center for high voltage measurement	2023-06-29
4	800kV impulse voltage generator	EETC02-0007	0~800 kV	$U_{rel}=0.019 k=2$ $U_{rel}=0.016 k=2$	National center for high voltage measurement	2023-05-27
5	400kV DC high voltage generator	EETC02-0008	0~400 kV	$U_{rel}=0.012 k=2$	National center for high voltage measurement	2022-08-18
6	Operating duty test system-voltage	EETC02-0009	0~10kV	$U_{rel}=0.004 k=2$	Beijing Aerospace measurement and testing technology institute	2023-01-06
7	Partial discharge test system	EETC02-0043	/	$U_{rel}=0.013 k=2$	China Inspection Southwest Measurement Co.,LTD	2023-08-24
8	MOA-II D.C. reference voltage detector	EETC02-0048	DC 0~9 kV	$U_{rel}=0.008 k=2$	National center for high voltage measurement	2023-04-18
9	Temperature measuring system	EETC02-0053	0-150 $^{\circ}$ C	$U_{rel}=0.2^{\circ}C k=2$	Hubei province meteorological metrological verification station	2022-12-05



Appendix C: Waveforms



Fig C.1 Lightning impulse current and residual voltage waveform (sample 301, shunt 0.025V/A, divider $K_d=206.8$)




Fig C.2 Switching impulse current and residual voltage waveform (sample 301, shunt 0.025V/A, divider $K_d=206.8$)




Fig C.3 Step impulse current and residual voltage waveform (sample 301, shunt 0.0267V/A, divider $K_d=59.8$)






Fig C.4 The 1st time of sample 304, Repetitive charge transfer withstand, 0.00192V/A




Fig C.5 Operating duty waveform, sample 201, $K_d=1590$




Fig C.6 Power-frequency voltage-versus-time test waveform, sample 204, $K_d=1590$

质
★
用






Fig C.7 Power-frequency voltage-versus-time test waveform, sample 205, $K_d=1590$




Fig C.8 Power-frequency voltage-versus-time test waveform, sample 206, $K_d=1590$




Fig C.9 Power-frequency voltage-versus-time test waveform, sample 208, $K_d=1590$




Fig C.10 Test to verify the dielectric withstand of the internal components of an arrester , sample 104



Appendix D: Visual and dimensional check




Fig D1: GHD-35BLQ-51/134 type arrester and resistor






Fig D2 : Dimensional drawing of GHD-35BLQ-51/134

